



US006312317B1

(12) **United States Patent**
Oguma

(10) **Patent No.:** **US 6,312,317 B1**
(45) **Date of Patent:** **Nov. 6, 2001**

(54) **METHOD FOR THE PRODUCTION OF GLASS PRODUCT**

(75) Inventor: **Hironori Oguma**, Tokyo (JP)

(73) Assignee: **Hoya Corporation**, Tokyo (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **09/594,077**

(22) Filed: **Jun. 15, 2000**

Related U.S. Application Data

(62) Division of application No. 09/053,520, filed on Apr. 2, 1998, now Pat. No. 6,093,484.

(30) **Foreign Application Priority Data**

Apr. 4, 1997 (JP) 9-86369

(51) **Int. Cl.**⁷ **B24B 1/00**; B29D 11/00; B29C 71/00

(52) **U.S. Cl.** **451/42**; 451/41; 65/92; 264/341; 216/24; 216/26

(58) **Field of Search** 451/41, 42, 32, 451/8; 106/3; 65/37, 92; 51/293, 307, 308; 216/24, 26; 264/341

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,673,746 * 7/1972 Highberg 451/41

3,685,218 * 8/1972 Gambale et al. 451/41
5,227,343 7/1993 Osuka et al. 501/77
5,242,868 9/1993 Hara 501/44
5,249,076 9/1993 Fujiwara et al. 501/44
5,603,654 * 2/1997 Hayashi 451/36
5,668,066 9/1997 Oguma et al. 501/45
5,793,544 8/1998 Ogihara et al. 359/885
6,093,484 * 7/2000 Oguma 428/312.2

FOREIGN PATENT DOCUMENTS

07070553A * 3/1995 (JP) .
627152A * 8/1978 (SU) .
1165699A * 7/1985 (SU) .

* cited by examiner

Primary Examiner—Deborah Jones

Assistant Examiner—Stephen Stein

(74) *Attorney, Agent, or Firm*—Nixon & Vanderhye

(57) **ABSTRACT**

Glass surfaces are produced having a highly polished surface by polishing with a glass polishing liquid having a pH approximating the pH of the glass being polished. The method provides highly polished, smooth, highly accurate glass surfaces suitable for use optical filters and solid camera devices and solid image sensors. Phosphate and fluorophosphate glass filters and the like so formed have hair-like surface flaws, if any, of a width of 7 μ m or less.

7 Claims, 1 Drawing Sheet

